

كلية المستقبل الجامعة

وزارة التعليم العالي والبحث العلمي
جمهورية العراق

Concrete Technology
Second year
Lecture :3

قسم هندسة تقنيات البناء والانشاءات

Building & Construction Technology Engineering
Department

Session: 2022 – 2023

Produced by:
Alaa Hussein Ali

Chemical composition of Portland cement

The primary materials used in Portland cement manufacture are mainly lime, Silica, alumina and iron oxide. These compounds interact with each other inside the oven to form more complex materials and compounds. These chemical reactions continue inside the oven until the chemical equilibrium state is reached, and as a result, The burning product of clinker contains four main compounds as shown in the table below

التركيب الكيميائي	الرمز الكيميائي المختصر	اسم المركب	ت
$2 \text{ CaO} \cdot \text{SiO}_2$	C_2S	سليكات ثنائي الكالسيوم	1
$3 \text{ CaO} \cdot \text{SiO}_2$	C_3S	سليكات ثلاثي الكالسيوم	2
$3 \text{ CaO} \cdot \text{Al}_2\text{O}_3$	C_3A	ألومينات ثلاثي الكالسيوم	3
$4 \text{ CaO} \cdot \text{Al}_2\text{O}_3 \cdot \text{Fe}_2\text{O}_3$	C_4AF	ألومينات الحديد رباعي الكالسيوم	4

These Symbols are obtained by means of the oxide symbols used by the cement chemists.

الرمز المختصر	الرمز الكيمياوي	الأكاسيد
A	Al_2O_3	أوكسيد الألمنيوم
C	CaO	أوكسيد الكالسيوم
F	Fe_2O_3	أوكسيد الحديد
S	SiO_2	أوكسيد السليكون

سليكات ثنائي الكالسيوم C2S, Di-Calcium Silicate

This compound is characterized by its **slow reaction speed** and **gives little heat during the reaction**, initial bearing to **resist compression is weak** , but its **final bearing is good**.

سليكات ثلاثي الكالسيوم C3S, Tri-Calcium Silicate

This compound is characterized by its **moderate reaction speed**, and give a **good amount of heat during the reaction**,

Initial and final bearing is good, and this compound was form with **C2S** is about **(60-80)%** of Portland cement.

الوميئات ثلاثي الكالسيوم C_3A , Tri-Calcium Aluminate

This compound is characterized by its **rapid reaction and release a large amount of heat during the reaction.** initial bearing compression is good , but its final bearing is **weak.** and this compound is a concern قلق, due to its great interaction with Salt مع تفاعله الكبير تلف او, Which leads to cement damage اضعاف الاسمنت.

Tetra-Calcium Aluminate Ferrite, C4AF

الوميئات الحديد رباعية الكالسيوم

It represents a group of oxides similar in properties to previous oxides, and reacts with water at a speed lower than C3A

Water compounds are **more stable than C3A** compounds and **less stable than** hydrated calcium silicate compounds. The hydration temperature is higher than that generated by C2S and less than the other compounds and is found by **(5-10)%** of the weight of cement.

- In addition to the four major compounds, there are other compounds with a very low percentage:

1. أوكسيد المغنيسيوم (MgO).

2. أوكسيد البوتاسيوم (K_2O).

3. أوكسيد الصوديوم (Na_2O).

4. أوكسيد المنغنيز (Mn_2O_3).

5. أوكسيد التيتانيوم (TiO_2).

6. ثالث أوكسيد الكبريت (SO_3).

7. الفسفور (P_2O_5).

In addition to the main compounds mentioned above, there exist minor compounds, such as **MgO**, **TiO₂**, **Mn₂O₃**, **K₂O** and **Na₂O**. Two of the minor compounds are of particular interest: K₂O and Na₂O, known as the **alkalis (about 0.4-1.3% by weight of cement)**. They have been found to react with the reactive silica found in some aggregates, the products of the reaction causing increase in volume leading to disintegration **تهشم او تحطم** of the concrete. Increase in the alkalis percentage has been observed to affect the setting time and the rate of the gain of strength of cement.

- **SO₃** form low percentage of cement weight. **SO₃** comes from the gypsum added (2-6% by weight) during grinding of the clinker, and from the impurities الشوائب in the raw materials, also from the fuel الوقود used through firing process.
- **Iraqi specification no. 5 limited max. SO₃ by 2.5% when C3A ≤ 7%, and by 3% when C3A > 7%.**

- **MgO**, present in the cement by **1-4%**, which comes from the magnesia compounds present in the raw materials. Iraqi specification no. 5 limited max. **MgO by 5%**, to control the expansion resulted from the hydration of this compound in the hardened concrete. When the magnesia is in amorphous form, it has no harmful effect on the concrete.
- **Other minor compounds such as TiO₂, Mn₂O₃, P₂O₅** represent **< 1%**, and they have little importance.

- The percentage of the main composition of cement can be calculated according to the Bogue equations, based on the assumption that the reactions reached the chemical equilibrium state

$$C_3S = 4.07 (\text{CaO}) - 7.6 (\text{SiO}_2) - 6.72 (\text{Al}_2\text{O}_3) - 1.43 (\text{Fe}_2\text{O}_3) - 2.85 (\text{SO}_3)$$

$$C_2S = 2.87(\text{SiO}_2) - 0.754 (C_3S)$$

$$C_3A = 2.65 (\text{Al}_2\text{O}_3) - 1.69 (\text{Fe}_2\text{O}_3)$$

$$C_4AF = 3.04 (\text{Fe}_2\text{O}_3)$$

Usual Composition Limits of Portland Cement

Oxide	Content, %
CaO	60-67
SiO ₂	17-25
Al ₂ O ₃	3-8
Fe ₂ O ₃	0.5-6
MgO	0.5-4
Alkalis (as Na ₂ O)	0.3-1.2
SO ₃	2.0-3.5

Typical compound composition in ordinary Portland cement

Compound	Content, %
C_3S	54
C_2S	17
C_3A	11
C_4AF	9

• **Loss on Ignition (L.O.I)**

It is the loss of the cement sample weight when it expose to the **red temperature (at 1000°C)**. It shows the extent of carbonation and hydration of free lime and free magnesia due to the exposure of cement to the atmosphere. Also, part of the loss in weight comes from losing water from the gypsum composition. The maximum loss on ignition permitted by Iraqi specification no. 5 is 4% by weight.

هو الفقدان في وزن النموذج بعد التسخين الى درجة الحرارة الحمراء (Red Heat) 1000 م°،
ويعبر عن مقدار الكربنة (Carbonation)، وعن عملية الأماهة (Hydration Process) التي
تحدث للجير الحر (Free Lime) والمغنيسيا الحرة الموجودين في السمنت نتيجة خزن السمنت

لفترة طويلة (Prolonged Story)، أو نتيجة تعرضه للظروف الجوية، كما وأن جزءاً صغيراً من
الفقدان أثناء الأيقاد ناتج عن فقدان الماء الداخل في تركيب الجبس وتحدد المواصفات القياسية
البريطانية نسبة الفقدان أثناء الأيقاد من 3% في المناخ المعتدل، الى 4% في المناخ الأستوائي، أما
المواصفات القياسية العراقية فتحدد نسبة الفقدان للسمنت البوتلاندي الأعتيادي والسريع التصلب
بـ 4% كحد أقصى.

- **Insoluble residue**

It is that part of cement sample that is insoluble in HCl. It comes from the unreacted silica, to form soluble cement compounds in this acid, largely arising from impurities in gypsum. The maximum insoluble residue permitted by Iraqi specification no. 5 is 1.5% by weight.

- هي ذلك الجزء من نموذج السمنت الغير قابل للذوبان في حامض الهيدروكلوريك، وتنشأ بصورة رئيسية من السليكا غير المتفاعلة لتكوين مركبات السمنت الذائبة في هذا الحامض، لذا فإن المخلفات غير الذائبة تعبر عن مدى أكمال التفاعلات الكيميائية في داخل الفرن، والمواصفات القياسية العراقية تحدد نسبة المخلفات غير الذائبة ب 1.5 % من وزن السمنت كحد أقصى

*THANK YOU FOR
YOUR ATTENTION*

*YOUR ATTENTION
THANK YOU FOR*